

CLAIMS

Having sufficiently described the invention, that which is claimed is:

- 5
1. A seamless steel tube of high mechanical resistance, good degree of toughness, good resistance to cracking in the metal base and the heat affected zone (HAZ) and good corrosion resistance, characterized by the material of which it is manufactured being made up basically of Fe and the following chemical composition expressed in % by weight of additional elements:
- 10

C 0.06 to 0.13

15 Mn 1.00 to 1.30

Si 0.35 Max..

P 0.015 Max.

S 0.003 Max.

Mo 0.1 to 0.2

20 Cr 0.10 to 0.30

V 0.050 to 0.10

Nb 0.020 to 0.035

Ni 0.30 to 0.45

Al 0.015 to 0.040

25 Ti 0.020 Max.

BEST AVAILABLE COPY

N 0.010 Max.

Cu 0.2 Max.

And also the chemical composition with the following relation
among the alloying elements.

$$0.5 < (Mo + Cr + Ni) < 1;$$

$$(Mo + Cr + V)/5 + (Ni + Cu)/15 \leq 0.14$$

2. A seamless steel tube with high mechanical resistance, good hardness, good resistance to cracking in the metal base and in the HAZ, and good corrosion resistance as in Claim 1, also characterized by a Titanium content of no more than 0.002% by weight.

3. A seamless steel tube with high mechanical resistance, good hardening, good resistance to cracking in the metal base and in the HAZ, and good corrosion resistance as in Claims 1 and 2, also characterized by the presence of a resistance to cracking measured by the CTOD test at a temperature of $-40^{\circ}\text{C} \geq 0.8$ mm in the metal base and a CTOD test at a temperature of $0^{\circ}\text{C} \geq 0.5$ mm in the heat affected zone.

4. A seamless steel tubing with high mechanical resistance, good hardening, good resistance to cracking in the metal base and

in the HAZ, and good corrosion resistance as in Claims 1, 2 and 3, characterized by the resistance to corrosion measured by the HIC test in accordance with norm NACE TM0284 with solution A being 1.5% max. for CTR and 5.0% max. for CLR.

5
10 5. A seamless steel tubing with high mechanical resistance, good hardening, good resistance to cracking in the metal base and in the HAZ, and good corrosion resistance as in Claims 1-4, characterized by having heavy gauge walls ≥ 30 mm.

15 6. A seamless steel tubing with high mechanical resistance, good hardening, good resistance to cracking in the metal base and in the HAZ, and good corrosion resistance as in the previous claim, characterized by having heavy gauge walls ≥ 40 mm.

20 7. A seamless steel tubing with high mechanical resistance, good hardening, good resistance to cracking in the metal base and in the HAZ and good corrosion resistance as in any of the previous claims 1- 6, characterized by possessing the following properties:

YS_{Troom} ≥ 65 Ksi

YS_{130°C} ≥ 65 Ksi

25 UTS_{Troom} ≥ 77 Ksi

UTS $_{130^{\circ}\text{C}} \geq 77 \text{ Ksi}$

The energy absorbed was evaluated at a temperature of up to -10°C
 $\geq \text{Joules}$

5 Hardness $\leq 240 \text{ HV10}$ maximum

8. A seamless steel tubing with high mechanical resistance, good hardening, good resistance to cracking in the metal base and in the HAZ and good corrosion resistance as in any of the previous claims 1-7, characterized by possessing the following properties:

YS $T_{\text{room}} \geq 65 \text{ Ksi}$

YS $_{130^{\circ}\text{C}} \geq 65 \text{ Ksi}$

15 UTS $T_{\text{room}} \geq 77 \text{ Ksi}$

UTS $_{130^{\circ}\text{C}} \geq 77 \text{ Ksi}$

YS/UTS ≤ 0.89

Elongation $\geq 20\%$

20 Energy absorbed evaluated at a temperature of up to $-20^{\circ}\text{C} \geq 380$
 Joules

Shear Area at $-10^{\circ}\text{C} = 100\%$

Hardness $\leq 220 \text{ HV10}$

9. A process for manufacturing the seamless steel tubing with high mechanical resistance, good toughness, good resistance to cracking in the metal base and in HAZ and good corrosion resistance made up of steps: 1. Manufacturing the steel; 2. Obtaining the solid cylindrical piece; 3. Perforating said piece; 4. Laminating said steel piece; 5. Subjecting the laminated tubing to heat treatment, characterized said process by the addition of certain amounts of elements during the manufacturing and the elimination of other elements so as to produce a final composition in % by weight that contains, besides iron and inevitable impurities, the following:

C	0.06 to 0.13;
Mn	1.00 to 1.30;
Si	0.35 Max.;
P	0.015 Max.;
S	0.003 Max.;
Mo	0.01 to 0.20;
Cr	0.10 to 0.30;
V	0.050 to 0.10;
Nb	0.020 to 0.035;
Ni	0.30 to 0.45;
Al	0.015 to 0.040;
Ti	0.020 Max.;
N	0.010 Max.;

Cu 0.2 Max.

and also by the chemical composition complying with the relationship among the alloying elements:

5

$$0.5 \leq (\text{Mo} + \text{Cr} + \text{Ni}) < 1;$$

$$(\text{Mo} + \text{Cr} + \text{V})/5 + (\text{Ni} + \text{Cu})/15 \leq 0.14.$$

10

10. A process for manufacturing seamless steel tubing as claimed in the previous claim characterized by said heat treatment consisting of austenitizing to a temperature of between 900 and 930° C, followed by interior-exterior hardening in water and then heat treatment for tempering at a temperature of between 630 and 690° C as defined by the following equation:

15

$$T_{\text{Temp}} (^{\circ}\text{C}) = [-273 + 1000 / (1.17 - 0.2 \text{ C} - 0.3 \text{ Mo} - 0.4 \text{ V})]$$

+/- 5

20

25

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.